

Product Technical Data PATPOL 19-01

01. Description

PATPOL 19-01 is formulated to give tack free finish with filler after drying. It also take optimize level of filler loading and featured to maximum shelf life in metal containers for putty.

02. Application

Making of cat patch putty.

03. Physical data in the liquid state (conforms to IS 6746 –1994)

<i>Property</i>	<i>Unit</i>	<i>Limits</i>	<i>Test method</i>
Appearance	--	Pale Yellow Clear Liquid	--
Specific Gravity	--	1.13±0.05	--
Viscosity at 25°C - Brookfield LVT (2/30)	Mpa.s (cPs)	450±50	--
Acid Value	Mg KOH/g	22±2	--
Non-Volatiles Content	%	67±2	--
Gel Time @ 30°C*	Minutes	22±2	--
Peak Exotherm	°C	182±10	--
Stability in the dark at 30°C	Months	2	--

*Using 1.5%Co (3%), 1.5% MEKP (50%)

04. Properties of cast resin laminate-AVAILABLE ON REQUEST

05. Post curing

Mature the laminate for 24 hours @ room temperature, followed by post curing @ 60°C for 16 hours or @ 80°C for 3 hours

06. Usage

PATPOL 19-01 performs best if the laminate is completely post cured. The quantity of catalyst and accelerator may be adjusted to get the optimum gel time. Since viscosity increases on the storage, styrene may be added to lower viscosity

07. Storage

PATPOL 19-01 remains stable for 2 months at 30°C in the dark. The stability deteriorates markedly at elevated temperatures, especially when exposed to direct sunlight

08. Packing

PATPOL 19-01 is packed in HDPE carboys (35 kg) & epoxy coated steel drums (225 kgs)

.....
The information provided in this data sheet is to the best of our knowledge. We are not responsible for the accuracy of results obtained by the user, nor do we take any responsibility for any damages resulting from

the use of the data contained herein. We cannot guarantee protection against any possible action arising out of violation of IPR, directly or indirectly caused by the use of information contained herein.